## **Arcaloy 436**

## **Application**

- Arcaloy 436 is composed with 17% Cr and more excellent resistance to intergranular corrison than Arcaloy 409Ti. So that, it is very useful to welding of front pipe, flexible pipe, center pipe, tail pipe in car muffer stainless steel.
- It has excellent weldability, and good slag removal.

	Optimum	Parameters	Operating Range	
Wire Dia.	Amperes	Volts	Amperes	Volts
0.045"	240	27~28	200~275	24~30
0.052"	270	29~30	225~300	26~32

## Typical Mechanical Properties of All Weld Metal

	Yield Point N/mm²{kgf/mm²}	Elongation (%)	PWHT	
ĺ	392 {40}	15	850 ℃ X2hrs	

## Typical Undiluted Weld Metal Analysis %

С	Mn	Si	Р	S	Cr	Мо	Cu	Ti
0.023	0.45	0.32	0.011	0.007	16.7	0.92	0.02	0.62

